Technical datasheet

Coverlys TR135 C1

Agrotextiles - PE coated woven coverings

Beaulieu International Group

Technical Textiles

Functions

Coverlys TR135 C1 is a single coated PE fabric protecting fruit en vegetables against extreme climate conditions (rain, temperature and hail)

Coverlys TR135 C1 is a high quality product thanks its extreme strength and UV stabilization

Coverlys TR135 C1 is produced on a 4 meter-width (unsealed)

Product Specifications

| PROPERTIES | TEST METHOD | VALUE | | UNIT | TOLERANCE |
|-----------------------|-------------|-------------|------|------|-----------|
| | | WARP | WEFT | | |
| MATERIAL | | PE | PE | | |
| TISSUE COLOUR | | transparent | | | |
| TOTAL WEIGHT | | 135 | | g/m² | ± 5 % |
| TISSUE WEIGHT | ISO 3801 | 100 | | g/m² | ± 5 % |
| COATED SIDES | | 1 | | | |
| COATING MATERIAL | | LD-PE | | | |
| COATING WEIGHT / SIDE | ISO 2286 | 35 | | g/m² | ± 5 % |
| COATING COLOUR | | transparent | | | |
| WIDTH | | on request | | cm | ± 2 cm |
| LENGTH | | 100 - 1000 | | m | ± 2 % |

Technical characteristics

| PROPERTIES | TEST METHOD | VALUE | | UNIT | TOLERANCE | | | |
|--------------------|---|-------|------|-------|-----------|--|--|--|
| | | WARP | WEFT | _ | | | | |
| BREAK ELONGATION | ISO 13934-1 | 21 | 19 | % | ± 20 % | | | |
| TENSILE STRENGTH | ISO 13934-1 | 900 | 800 | N/5cm | ± 20 % | | | |
| UV-STABILIZATION | ISO 4892-3 cycle 3 | ≅ 400 | | kLy | | | | |
| SHRINKAGE | 15' à 70 °C | 1,5 | 1,5 | % | MAX | | | |
| LIGHT TRANSMISSION | | 80 | | % | | | | |
| REMARKS | UV-Stabilization : Based on QUV testing min 3700 h (cycles of 5 h light exposure UV-A 340 nm 0,83 W/m ² at 50°C and 1 h water spray), which corresponds theoretically to a solar irradiation of 400 kLY. In a climate zone of 90 kLy/y (Western Europe) this corresponds to 4-5 years. | | | | | | | |

This information contained in this document is based on testing carried out by our laboratory or external research institutes and literature data, and based on Mean Values. This TDS is valid until further notice. To the best of our knowledge and at the time of publication, this information is true and accurate. It shall however, in no event be held to constitute or imply warranty undertaking express or implied commitment from the part of Beaulieu International Group – Division Beaulieu Technical Textiles. No liability whatever can be accepted by Beaulieu International Group – Division Beaulieu Technical Textiles with regard to the handling, processing or use of the product concerned which must in all cases be used in accordance with all applicable laws and regulations. The mentioned characteristics are not valid when the fabric has been in contact with sulphur-, chlorine-, iron- and brominederivates, as well as with copper sulphates and if the product is not installed and used in strict accordance with the installation instructions.