

TECHNICAL DATASHEET

Terralys LF 35/35

Terralys LF 35/35 is a polypropylene woven slit film geotextile, manufactured into a dimensionally stable network, ensuring that filaments retain their relative positions.

Terralys LF 35/35 is inert to biological degradation, and resists most chemicals, alkali and acids encountered in natural soils.

Mechanical properties	Test method	MARV ENGLISH	MARV METRIC
Grab Tensile Strength (MD x CMD)	ASTM D4632	180 lbs x 170 lbs	800 N x 760 N
Grab Tensile Elongation (MD x CMD)	ASTM D4632	18 % x 14%	18 % x 14%
Trapezoid Tear Strength MD	ASTM D4533	100 lbs x 90 lbs	450 N x 400 N
CBR Puncture	ASTM D6241	675 lbs	3000 N
Permittivity	ASTM D4491	0.60 sec ⁻¹	0.60 sec ⁻¹
Water Flow Rate	ASTM D4491	45 gal/min/ft ²	1800 L/min/m ²
Apparent Opening Size*	ASTM D4751	20 US Std. Sieve	0.70 mm
UV Resistance (500 hrs)	ASTM D4355	80 %	80 %

*Maximum roll average value

Descriptive characteristics	Test method	TYPICAL ENGLISH	TYPICAL METRIC
Mass per unit area	ASTM D5261	4.0 oz/y ²	137 g/m ²

Note: The values presented in the tables above are indicative, they are offered solely to provide possible suggestions. We reserve the right to alter the results of these materials without prior notice. As the installation and the conditions of use are beyond our control, Beaulieu Technical Textiles cannot accept responsibility for the performance of any of these products. The properties listed herein are provided as information only and in no way can create any warranty.